

Technical Data: EURO BASIC 80 g/m²

Grammage	g/m ²	ISO 536	80	± 3.0
Caliper	mm/1000	ISO 534	106	± 4
Stiffness L&W	MD	ISO 2493	122	± 22
Stiffness L&W	CD	ISO 2493	55	± 15
Roughness Bendtsen	ml/min	ISO 8791-2	200	± 50
Opacity	%	ISO 2471	90.0	min
Moisture	%	ISO 287	4.6	± 0.6
Relative Humidity	%		30	± 5
Brightness with UV	D65	ISO 2470	103.5	± 1.5
CIE Whiteness		ISO 11475	146	± 3.0

Product meets EN 12281, requirements for copy paper for dry toner imaging processes and ISO 9706, requirements for permanence for paper. Production processes certified according to ISO 9001, 14001 and 18001.

IGNIFICANCE OF VALUES: 2 SIGMA

05/10/2009